42

PATCHWORK

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufted 1/10” Loop , printed Tufté 1/10” Bouclé , imprimé Getuftet 1/10” Schlinge , gedruckt Getuft 1/10” Luspool, bedrukt
PILE MATERIAL COUCHE D’USURE POLMATERIAL POOLMATERIAAL	100% PA 6 IMPREL
SECONDARY BACKING DOSSIER RÜCKENAUSSTATTUNG RUG	Back2Back: Modified bitumen enhanced with a thermoplastic elastomer, reinforced with a glass fibre fleece covered with 100% PES fleece. 10% recycled content included
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	Ca. 4400 g/m²
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	Ca. 605 g/m²
PILE ABOVE BACKING POIDS DE VELOURS UTILE POLNUTZSCHICHTGEWICHT NUTTIG POOLGEWICHT	Ca. 372 g/m²
TOTAL HEIGHT EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	Ca. 6,6 mm
PILE HEIGHT EPAISSEUR DU VELOURS POLDICKE POOLHOOGTE	Ca. 3,1 mm
PILE DENSITY DENSITÉ DU VELOURS POLROHDICHTE POOLDICHTHEID	Ca. 0,120 g/cm³
TUFT DENSITY NOMBRE DE TOUFFES NOPPENZAHL AANTAL PUNTEN	Ca. 218.000 /m²
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 33- LC1
CASTOR CHAIR SUITABILITY EMPLOI CHAISE À ROULETTES STUHLROLLENEIGNUNG ROLSTOELGESCHIKTHEID	EN 985 A : continuous use
DONNÉES ENVIRONNEMENTALES	Démarche HQE® : cf. FDES suivant NF P01-010 Déclaration du 30/07/2003

FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 B_{fl}-s1
FASTNESS TO LIGHT SOLIDITÉ À LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	ISO 105-B02 ≥5-6
RUBBING FASTNESS SOLIDITÉ AU FROTTEMENT REIBECHTHEIT WRIJFECHTHEID	EN ISO 105-X12 ≥4
COLOUR FASTNESS TO WATER SOLIDITÉ À L’EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥4
THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLABWIDERSTAND WARMTEDOORLAATWEERSTAND	ISO 8302 0,063 m²K/W
IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNGMAB GELUIDSISOLATIE	ISO 10140 ΔL: 32 dB (1 000 Hz) ΔL_w: 23 dB
SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUIDSABSORPTIE	ISO 354 α_w: 0,15 Hz 125 250 500 1000 2000 4000 α_s 0,00 0,00 0,06 0,15 0,28 0,31
PERMANENT ANTISTATIC ANTISTATIQUE PERMANENT PERMANENT ANTISTATISCH PERMANENT ANTISTATISCH	ISO 6356 ≤ 2 kV
TRANSVERSAL RESISTANCE RÉSISTANCE TRANSVERSALE DURCHGANGSWIDERSTAND DOORGANGSWEERSTAND	ISO/DIS 10965 ≤ 1 x 10^9 Ohm
SIZE & PACKING DIMENSION & EMBALLAGE ABMESSUNG & VERPACKUNG AFMETINGEN & VERPAKKING	50 cm x 50 cm box: 5m² pallet: 20 boxes
NUMBER OF COLOURS NOMBRE DE COLORIS ANZAHL DER FARBEN AANTAL KLEUREN	6, Special colours possible Coloris spéciaux possible Sonderfarben möglich Speciale kleuren mogelijk
DIMENSIONAL STABILITY STABILITÉ DIMENSIONNELLE DIMENSIONSTABILITÄT DIMENSIONELE STABILITEIT	EN 986 max. 0,2 %
GUT-NR	3CBEDAF8
LEED®	Product contributes toward satisfying Credits under LEED®.*

We reserve all rights for technical improvements | Technische wijzigingen, de verbetering van het product, worden voorbehouden | Sous réserve de toute modification technique visant à l’amélioration constante de nos produits | Durch technische Weiterentwicklung sind Änderungen vorbehalten

* For more information, see the modulyss sustainability statements. Remark: Products are not reviewed under LEED®. LEED® credit requirements cover the project level and are evaluated by the building owner. Modulyss® products can contribute to the accepted benchmark for the design, construction and operation of green buildings. For more information on LEED®, visit www.usgbc.org/contact.





modulyss®
Zevensterrestraat 21
B 9240 Zele
T +32 (0)52 80 80 80
F +32 (0)52 80 82 00
info@modulyss.com
www.modulyss.com